

PCM

Peelable Coating Mask

DESCRIPTION

PCM is a flexible, solvent resistant latex for masking components, connectors, and other items during the conformal coating process. The high film strength of **PCM** means that it can be peeled by hand without breaking or leaving residues.

READ ENTIRE TECHNICAL BULLETIN BEFORE USING THIS PRODUCT

FEATURES AND BENEFITS

- Flexible latex with high film strength; leaves no residue even when removed from complex areas
- Allows selective coating of circuit boards, masks components and connectors during coating application
- Prevents coating ingress into connectors and components due to the capillary effect
- Suitable for use with dip, spray or brush applied conformal coatings

APPROVALS

Standard	Status
RoHS Compliant (2015/863/EU)	Yes

PRODUCT INFORMATION

For available packaging sizes please visit:

electrolube.com

PHYSICAL PROPERTIES

Category	Results
Liquid Properties	
Density @ 20 °C (g/mL)	1.11
Solid Content	70 to 74 %
Viscosity Brookfield LVT (mPa s)	30,000 to 60,000
Ammonia Content	0.29% Max
pH	10 to 11
Drying Time (2 mm Thickness)	
25 °C	2 hours
60 °C	30 minutes
Cured Properties	
Tensile Strength (MN/m ²)	16.57
Elongation at Break	900 %
Modulus	
@ 300% (MN/m ²)	0.88
@ 700% (MN/m ²)	6.18

APPLICATION GUIDELINES

Masking should take place between the cleaning and coating process. PCM should be applied to the area being masked to a thickness of at least 1mm to enable easy peeling after coating. Dry at room temperature for at least 2 hours. This can be accelerated by heating to 60 °C for 30 minutes but some discolouration of copper may occur.

Thicker films may require longer drying times. As PCM dries it darkens in colour. PCM must be fully dry before being coated. After spray, dip, or brush application with conformal coating the coating should be air-dried in accordance with manufacturer's recommendations before PCM is removed.

When the coating is dry, peel off PCM by hand to leave the protected area or component clean and free from coating. The conformal coating may then be heat cured if applicable.

Note: This product contains Ammonia. It should be applied and allowed to dry in a well-ventilated area. Store below 30 °C (between 10 °C and 25 °C is ideal) in original container.

ADDITIONAL INFORMATION

Shelf Life: 12 Months

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

To confirm this document is the most recent version, please contact
TechnicalSupportTeam@hkw.co.uk
www.electrolube.com

North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460	Europe Ashby Park Coalfield Way Ashby de la Zouch Leicestershire, LE65 1JR, UK 44.01530.41960	Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100
--	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.